

Amendments to the Claims:

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Original) A method for preparing an amorphous metal fluoride of the formula $M^{x+}F_{x-\delta}$ comprising the steps of

- a) providing a precursor, whereby the precursor comprises a structure having a formula of $M^{x+}F_{(x-\delta)-y}B_y$; and
- b) reacting the precursor with a fluorinating agent generating the amorphous metal fluoride having a formula of $M^{x+}F_{x-\delta}$.


whereby M is selected from the group comprising metals of the second, third and fourth main group and any subgroup of the periodic table, Zn, Sn, Cu, Fe
Cr, V, Mg, Al
 B is a coordinately bound group;
 x is any integer of 2 or 3;
 y is any integer between 1 and 3;
 δ is 0 to 0.1; and
 $x-\delta > y$.

2. (Original) The method according to claim 1, wherein B is selected from the group comprising alkoxides, enolates and salts of carboxylic acid having preferably a length of 1 to 5 C atoms.

3. (Currently Amended) The method according to ~~any of claims 1 to 2~~ claim 1, wherein the precursor, the starting material for the precursor or the fluorinating agent is present in or introduced into an anhydrous organic solvent, whereby the anhydrous organic solvent is

obj
preferably selected from the group comprising alcohols, ethers, ketones, alkanes, formic acid, acidic acid and propionic acid.

4. (Currently Amended) The method according to ~~any of claims 1 to 3~~ claim 1, wherein the precursor contains or is made from a compound of the formula



imdc
whereby M, F, x, y, δ and B are defined as in any of the preceding claims;
L is a solvent, preferably a solvent as specified in claim 3; and
d is ≤ 1 .

} proper?

5. (Currently Amended) The method according to ~~any claims 1 to 4~~ claim 1, wherein step b is carried out at a temperature below the crystallisation point of the amorphous metal fluoride.

6. (Currently Amended) The method according to ~~any of claims 1 to 5~~ claim 1, wherein the precursor is prepared by

- providing the metal component of the precursor as an anhydrous metal compound, preferably as $M^{x+}B_x$,

imdc
with M, B and x being defined as in any of the preceding claims, and

ok?

- reacting said metal component with anhydrous hydrogen fluoride.

7. (Currently Amended) The method according to ~~any of claims 1 to 6~~ claim 1, wherein the fluorinating agent is $CH_3Cl_hF_{4-g-h}$ with the sum of g+h being equivalent to 1 to 3.

12
8. (Currently Amended) The method according to ~~any of the claims 1 to 6~~ claim 1,

wherein the fluorinating agent is HF.

9. (Currently Amended) The method according to ~~any of claims 1 to 8~~ claim 1, wherein the amorphous metal fluoride is a catalyst, preferably a heterogenous catalyst.

10. (Original) A method for the manufacture of a catalyst, preferably a catalyst comprising amorphous metal fluoride of the formula $M^{x+}F_{x-\delta}$,

whereby M is selected from the group comprising metals of the second, third and fourth main group and any subgroup of the periodic table,

x is any integer of 2 or 3; and

δ is 0 to 0.1,

comprising the steps of the method according to any of claims 1 to 8, wherein the amorphous metal fluoride is the catalyst.

11. (Currently Amended) An amorphous metal fluoride obtainable by a method according to ~~any of claims 1 to 9~~ claim 1.

12. (Currently Amended) A catalyst obtainable by a method according to ~~claims 9 or 10~~ claim 9.

13. (Original) A catalyst comprising amorphous metal fluoride of the formula $M^{x+}F_{x-\delta}$,

whereby M is selected from the group comprising metals of the second, third and fourth main group and any subgroup of the periodic table,

x is any integer of 2 or 3; and

130C

102

δ is 0 to 0.1,

which is catalytically active and preferably having an active surface of about 100-300 m²/g, preferably 180-280 m²/g.

14. (Currently Amended) An industrially producible catalyst, preferably a catalyst according to claim 12 ~~or 13~~, containing amorphous metal fluoride of the formula $M^{x+}F_{x-\delta}$.

whereby M is selected from the group comprising metals of the second, third and fourth main group and any subgroup of the periodic table,

x is any integer of 2 or 3, and

δ is 0 to 0.1,

being catalytically active and preferably having an active surface of about 100-300 m²/g, preferably 180-280 m²/g.

15. (Currently Amended) A moisture resistant catalyst, preferably a catalyst according to ~~any of claims 12 to 14~~ claim 12, containing amorphous metal fluoride of the formula $M^{x+}F_{x-\delta}$.

whereby M is selected from the group comprising metals of the second, third and fourth main group and any subgroup of the periodic table,

x is any integer of 2 or 3, and

δ is 0 to 0.1.

16. (Currently Amended) The catalyst according to ~~any of claims 12 to 15~~ claim 12, wherein M is selected from the group comprising Zn, Sn, Cu, Fe, Cr, V, Mg and Al, whereby preferably M has a charge of +2 or +3.

17. (Currently Amended) The catalyst according to ~~any of claims 12 to 15~~ claim 1, wherein any of M is used as $M^{x+}F_{x-\delta}$, as guest component or as host component.

18. (Original) A catalyst containing a metal fluoride of the formula $M^{x+}F_{x-\delta}$.

whereby M is selected from the group comprising metals of the second, third and fourth main group and any subgroup of the periodic table,

x is any integer of 2 or 3; and

δ is 0 to 0.1,

which catalyst is essentially free of Cl, whereby preferably the catalyst is a catalyst according to any of the preceding claims.

112 Obj. some of "preceding claims" are
methods (1-10)